

# italsenso

Data / Date

26.02.13

## SCHEMA TECNICA TECHNICAL CARD

Articolo / Article / <b>Tkanina</b>	<b>Sabbia</b>
Codice Articolo / Article Code / <b>Kod tkaniny</b>	<b>23002</b>
Composizione / Composition / <b>Kompozycja</b>	<b>90 % PL 10% CO</b>
Peso Gr/mtl / Weight Grs/lmt / <b>Waga gr/mtb</b>	<b>400</b>
Altezza cm / Width cms / <b>Szerokość cm</b>	<b>138/140</b>

### Odporność na ścieranie

Test Martindale

Colour degradation after 3000 rubs: 4/5

UNI EN ISO 12947 - 2

**100.000** Giri / Rubs / **Cykli**

EN 14465, appendix A

### Solidità Luce / Colour Fastness to light / **Odporność kolorów na światło**

UNI EN ISO 105-B02

**4/5**

Blue Scale 1/8

### Solidità Sfregamento / Colour Fastness to rubbing / **Odporność kolorów na pocieranie**

UNI EN ISO 105-X12

**4/5**

Secco / Dry / **Sucho**

Gray Scale 1/5

**3/4**

Umido / Wet / **Mokro**

### Odporność na Pilling

Test Pilling

UNI EN ISO 12945-2

Degradation average photographic scale 1/5:

**4/5**

### Manutenzione / Maintenance



Note/Notes: Dimensional stability to dry washing (UNI EN ISO 3175)

warp: +/- % weft: +/- %

Dimensional stability to washing (UNI EN ISO 6330)

warp: +/- % weft: +/- %

\* The results are tested in the laboratory and they must be considered as indicative.

ITALVELLUTI Polska Sp. z o.o.  
33-386 Podegrodzie, Brzezna 495  
tel. 18 446 07 84 fax. 18 414 54 51  
e-mail: [italvelluti@italvelluti.pl](mailto:italvelluti@italvelluti.pl)  
[www.italvelluti.eu](http://www.italvelluti.eu)

italvelluti