

## SCHEDA TECNICA TECHNICAL CARD

Articolo / Article / <b>Tkanina</b>	Diamond
Composizione / Composition / <b>Kompozycja</b>	48% PL 40% CO 12% VI
Peso Gr/mtl / Weight Grs/lmt / <b>Waga gr/mtb</b>	781
Altezza cm / Width cms / <b>Szerokość cm</b>	138/140

### Odporność na ścieranie

Test Martindale	Colour degradation after 3000 rubs:
UNI EN ISO 12947 - 2	<b>100 000</b> Giri / Rubs / <b>Cykli</b>
EN 14465, appendix A	

### Solidità Luce / Colour Fastness to light / **Odporność kolorów na światło**

UNI EN ISO 105-B02	<b>4/5</b>
Blue Scale 1/8	


### Solidità Sfregamento / Colour Fastness to rubbing / **Odporność kolorów na pocieranie**

UNI EN ISO 105-X12	<b>4</b> Secco / Dry / <b>Sucho</b>
Gray Scale 1/5	<b>3/4</b> Umido / Wet / <b>Mokro</b>

### Odporność na Pilling

Test Pilling	Degradation average photographic scale 1/5:	<b>4</b>
UNI EN ISO 12945-2	a 2000 giri / at 2000 revs	

### Manutenzione / Maintenance / **Sposób czyszczenia**



Note/Notes: Dimensional stability to dry washing (UNI EN ISO 3175)  
**Stabilność wymiaru przy praniu chemicznym (UNI EN ISO 3175)**  
warp / wątek: +/- % weft / osnowa: +/- %  
Dimensional stability to washing (UNI EN ISO 6330)  
**Stabilność wymiaru przy praniu wodnym (UNI EN ISO 6330)**  
warp / wątek: +/- % weft / osnowa: +/- %

\* The results are tested in the laboratory and they must be considered as indicative.

ITALVELLUTI Polska Sp. z o.o.  
33-386 Podegrodzie, Brzezna 495  
tel. 18 446 07 84 fax. 18 414 54 51  
e-mail: [italvelluti@italvelluti.pl](mailto:italvelluti@italvelluti.pl)  
[www.italvelluti.eu](http://www.italvelluti.eu)

italvelluti