

# italsenso

Data / Date

01.07.2022

## SCHEDA TECNICA TECHNICAL CARD

Articolo / Article / <b>Tkanina</b>	<b>Cavallo</b>
Composizione / Composition / <b>Kompozycja</b>	<b>100% PL</b>
Peso Gr/mtl / Weight Grs/lmt / <b>Waga gr/mtb</b>	<b>630</b>
Altezza cm / Width cms / <b>Szerokość cm</b>	<b>138/140</b>

### Odporność na ścieranie

Test Martindale                      Colour degradation after 3000 rubs:  
UNI EN ISO 12947 - 2                      **100 000**                      Giri / Rubs / **Cykli**  
EN 14465, appendix A

### Solidità Luce / Colour Fastness to light / **Odporność kolorów na światło**

UNI EN ISO 105-B02                      **3/4**  
Blue Scale 1/8


### Solidità Sfregamento / Colour Fastness to rubbing / **Odporność kolorów na pocieranie**

UNI EN ISO 105-X12                      **4/5**                      Secco / Dry / **Sucho**  
Gray Scale 1/5                      **4**                      Umido / Wet / **Mokro**

### Odporność na Pilling

Test Pilling                      Degradation average photographic scale 1/5:                      **4/5**  
UNI EN ISO 12945-2                      a 2000 giri / at 2000 revs

### Manutenzione / Maintenance / **Sposób czyszczenia**



Note/Notes: Dimensional stability to dry washing (UNI EN ISO 3175)  
**Stabilność wymiaru przy praniu chemicznym (UNI EN ISO 3175)**  
warp / wątek: +/- % weft / osnowa: +/- %  
Dimensional stability to washing (UNI EN ISO 6330)  
**Stabilność wymiaru przy praniu wodnym (UNI EN ISO 6330)**  
warp / wątek: +/- % weft / osnowa: +/- %

\* The results are tested in the laboratory and they must be considered as indicative.

ITALVELLUTI Polska Sp. z o.o.  
33-386 Podegrodzie, Brzezna 495  
tel. 18 446 07 84 fax. 18 414 54 51  
e-mail: [italvelluti@italvelluti.pl](mailto:italvelluti@italvelluti.pl)  
[www.italvelluti.eu](http://www.italvelluti.eu)

italvelluti